

Plain bearings — Wrapped bushes —

Part 4: Materials

Licensed Copy: :FULLNAME, : DATE, Uncontrolled Copy, (c) BSI

ICS 21.100.10

National foreword

This British Standard was published by BSI. It is the UK implementation of ISO 3547-4:2006. It supersedes BS ISO 3547-4:1999 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee MCE/12, Plain bearings.

A list of organizations represented on MCE/12 can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 November 2006

© BSI 2006

ISBN 0 580 49526 4

Amendments issued since publication

Amd. No.	Date	Comments

INTERNATIONAL
STANDARD

ISO
3547-4

Second edition
2006-10-15

Plain bearings — Wrapped bushes —
Part 4:
Materials

Paliers lisses — Bagues roulées —
Partie 4: Matériaux



Reference number
ISO 3547-4:2006(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 3547-4 was prepared by Technical Committee ISO/TC 123, *Plain bearings*, Subcommittee SC 3, *Dimensions, tolerances and construction details*.

This second edition cancels and replaces the first edition (ISO 3547-4:1999), which has been technically revised.

ISO 3547 consists of the following parts, under the general title *Plain bearings — Wrapped bushes*:

- *Part 1: Dimensions*
- *Part 2: Test data for outside and inside diameters*
- *Part 3: Lubrication holes, grooves and indentations*
- *Part 4: Materials*

The following parts are under preparation:

- *Part 5: Checking the outside diameter*
- *Part 6: Checking the inside diameter*
- *Part 7: Measurement of wall thickness of thin-walled half-bearings and thin-walled bushes*

Plain bearings — Wrapped bushes —

Part 4: Materials

1 Scope

This part of ISO 3547 gives specifications for solid and multi-layer bearing materials, such as are used for wrapped bushes in accordance with the other parts of ISO 3547.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3547-1:2006, *Plain bearings — Wrapped bushes — Part 1: Dimensions*

ISO 3547-2, *Plain bearings — Wrapped bushes — Part 2: Test data for outside and inside diameters*

ISO 3547-3, *Plain bearings — Wrapped bushes — Part 3: Lubrication holes, grooves and indentations*

ISO 4378-1, *Plain bearings — Terms, definitions and classification — Part 1: Design, bearing materials and their properties*

ISO 4382-2, *Plain bearings — Copper alloys — Part 2: Wrought copper alloys for solid plain bearings*

ISO 4383, *Plain bearings — Multilayer materials for thin-walled plain bearings*

ISO 4384-1, *Plain bearings — Hardness testing of bearing metals — Part 1: Compound materials*

ISO 4384-2, *Plain bearings — Hardness testing of bearing metals — Part 2: Solid materials*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4378-1 apply.

4 Requirements

4.1 Chemical analysis

Chemical analysis shall be definitive for the acceptance of the bearing metals. Arbitrary analyses or random sampling operations shall be performed in accordance with recognized methods and agreed between the supplier and user.

4.2 Hardness values

The hardness values indicated in Tables 1 and 2 are typical for each of the materials concerned. In practice, composition and processing variables can result in significant variations in hardness. Hardness specifications shall be agreed between the supplier and user.

Table 1 — Solid materials

Key	Designation ^a	Hardness ^b (guide values) HB 2,5/62,5/10	Notes relating to use	Wall thickness limit deviation series ^c
Z1	Steel (hardened)	—	Suitable for secondary applications with lightly loaded sliding characteristics.	A
Y1	CuSn8P	120	Very high load capacity, good antifrictional property, e.g. for vehicles, transmissions, conveyor systems and agricultural machinery.	A, C, W
Y2		150		
W1	CuZn31Si	110	High load capacity, good antifrictional properties, e.g. for textile machinery, motor vehicles and agricultural machinery and lifts.	
W2		140		

^a Steel composition shall be agreed between supplier and user. It will normally have a carbon content of less than 0,25 %; composition of bearing material in accordance with ISO 4382-2.

^b Hardness testing in accordance with ISO 4384-2.

^c In accordance with ISO 3547-1:2006, Tables 5 and 6.

Table 2 — Multi-layer materials

Key	Designation ^a		Hardness ^b (guide values)		Notes relating to use	d
	Backing material	Bearing material	Backing material ^c	Bearing material		
T2	Steel	SnSb8Cu4	130	17 HV to 24 HV	Very good emergency running characteristics, fair load capacity, e.g. for pumps, compressors, automatic transmissions, starters and camshafts.	A, C, W
S1	Steel	CuPb24Sn (cast)	125	55 HB to 80 HB	High load capacity, with hardened shafts being necessary as a rule, e.g. for automatic transmissions, steering assemblies, camshafts and pumps.	
S2	Steel	CuPb24Sn (sinter)	125	40 HB to 60 HB		
S3	Steel	CuPb24Sn4 (cast)	125	60 HB to 90 HB	As for the material with keys S1 and S2; more suitable for the embossing of grooves. Very high load capacity, with hardened shafts being necessary as a rule, e.g. for gudgeon pins and rocker arm bearings, transmission shafts, steering assemblies and pumps. Available with greater Brinell hardness for special applications.	
S4	Steel	CuPb24Sn4 (sinter)	125	45 HB to 90 HB		
S5	Steel	CuPb10Sn10 (cast)	125	70 HB to 130 HB		
S6	Steel	CuPb10Sn10 (sinter)	125	60 HB to 90 HB		
R1	Steel	AlSn6Cu	170	35 HB to 45 HB	High load capacity, with hardened shafts being necessary as a rule, e.g. for transmissions and hydraulic pumps.	A, C, W
R2	Steel	AlSn20Cu	170	30 HB to 40 HB	Good emergency running characteristics, fair load capacity, e.g. for refrigeration plant, compressors and pumps.	
R3	Steel	AlSn12SiCu	170	40 HB to 60 HB	High load capacity, good seizure resistance, e.g. for transmissions camshafts and hydraulic pumps.	
R4	Steel	AlZn5	185 HB	60 HB to 100 HB	Higher load capacity.	
P1	Steel	With porous sintered bronze, filler and surface coating (running-in coating) of PTFE with additives.	140	—	Low friction; for vehicle suspension struts, gear levers, pivot bearings, pumps and lifting magnets; operating range from – 200 °C to + 280 °C, but not suitable for machining in the bearing bore; suitable for use as a dry bearing material.	B
B1	Bronze		100			
P2	Steel	With porous sintered bronze coated with thermoplastic.	140	—	High load capacity, greased on assembly, e.g. for cranes, hoists, lifts, packaging machinery and agricultural machinery, some temperature limitation. ^e	D, E
B2	Bronze		100			

Table 2 (continued)

Key	Designation ^a		Hardness ^b (guide values)		Notes relating to use	d
	Backing material	Bearing material	Backing material ^c	Bearing material		
D1	Steel	With directly bonded polymer bearing lining, e.g. PTFE.	140	—	For specific applications where special properties are required, e.g. limited space, corrosion resistance.	B
D2	Stainless steel		140			
D3	Bronze		100			
D4	Aluminium alloy		60			

The materials S1 to S6 and R1 may be supplied with an additional running-in coating, for series A and W only, by agreement with the supplier.

^a Steel composition shall be agreed between the supplier and user. It will normally have a carbon content of less than 0,25 %; composition of bearing material in accordance with ISO 4383.

^b Hardness testing in accordance with ISO 4384-1.

^c Hardness for steel and stainless steel HB1/30/10.
Hardness for bronze and aluminium alloy HB1/5/30.

^d Wall thickness limit deviation series (in accordance with ISO 3547-1:2006, Tables 5 and 6).

^e Temperature limitation for continuous duty depends on type of thermoplastic, e.g. POM: 90 °C; PVDF: 110 °C; PEEK: 250 °C.

Bibliography

- [1] ISO 683-11, *Heat-treatable steels, alloy steels and free-cutting steels — Part 11: Wrought case-hardening steels*
- [2] ISO 6932, *Cold-reduced carbon steel strip with a maximum carbon content of 0,25 %*

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.